Starting Temper	Heat Treated Temper										
General Temper Conversions For 7075 Material	"0"	O1	T6	T651	T6511	T73	T7351	T73511	T76	T7651	T76511
"0"-Condition		No	Sol & Age	No	No	Sol & Age	No	No	Sol & Age	No	No
O1	Anneal		Sol & Age	No	No	Sol & Age	No	No	Sol & Age	No	No
T6	Anneal	No		No	No	Age Only	No	No	Age Only	No	No
T651	Anneal	No	Sol & Age		No	Sol & Age	Age Only	No	Sol & Age	Age Only	No
T6511	Anneal	No	Sol & Age	No		Sol & Age	No	Age only	Sol & Age	No	Age Only
T73	Anneal	No	Sol & Age	No	No		No	No	Sol & Age	No	No
T7351	Anneal	No	Sol & Age	No	No	Sol & Age		No	Sol & Age	No	No
T73511	Anneal	No	Sol & Age	No	No	Sol & Age	No		Sol & Age	No	No
T76	Anneal	No	Sol & Age	No	No	Sol & Age	No	No		No	No
T7651	Anneal	No	Sol & Age	No	No	Sol & Age	No	No	Sol & Age		No
T76511	Anneal	No	Sol & Age	No	No	Sol & Age	No	No	Sol & Age	No	

Starting Temper	Heat Treated Temper										
General Temper Conversions For 2024 Material	"0"	T3	T351	T3511	T4	T42	T6	T62	T81	T851	T8511
"0"-Condition		No	No	No	Sol & Age	Sol & Age	Sol & Age	Sol & Age	No	No	No
T3	Anneal		No	No	Sol & Age	Sol & Age	Sol & Age	Sol & Age	Age Only	No	No
T351	Anneal	No		No	Sol & Age	Sol & Age	Sol & Age	Sol & Age	No	Age Only	No
T3511	Anneal	No	No		Sol & Age	Sol & Age	Sol & Age	Sol & Age	No	No	Age Only
T4	Anneal	No	No	No		Sol & Age	Age Only	Sol & Age	No	No	No
T42	Anneal	No	No	No	Sol & Age		Sol & Age	Sol & Age	No	No	No
T6	Anneal	No	No	No	Sol & Age	Sol & Age		Sol & Age	No	No	No
T62	Anneal	No	No	No	Sol & Age	Sol & Age	Sol & Age		No	No	No
T81	Anneal	No	No	No	Sol & Age	Sol & Age	Sol & Age	Sol & Age		No	No
T851	Anneal	No	No	No	Sol & Age	Sol & Age	Sol & Age	Sol & Age	No		No
T8511	Anneal	No	No	No	Sol & Age	Sol & Age	Sol & Age	Sol & Age	No	No	

Starting Temper	Heat Treated Temper				
General Temper Conversions For 6061 Material	"0"	T4	T42	T6	T62
"0"-Condition		Sol & Age	Sol & Age	Sol & Age	Sol & Age
T4	Anneal		Sol & Age	Age Only	Sol & Age
T42	Anneal	Sol & Age		Sol & Age	Age Only
T6	Anneal	Sol & Age	Sol & Age		Sol & Age
T62	Anneal	Sol & Age	Sol & Age	Sol & Age	